



# Bostik® 70-08A / Simson ISR 70-08

## TECHNICAL DATA

Basic Material	Silyl Modified Polymer (SMP)
Curing Method	Moisture
Specific Gravity	ca. 1.4 g/ml
Skin Forming Time	ca. 10 min.
Open Time	< 15 min.
Curing Speed after 24 hrs	ca. 3 mm
Shore A Hardness	ca. 65
Volume Change	< 3%
Green Strength	ca. 1800 Pa
Electrical Volume Resistivity	(Maximum load which can be applied per m <sup>2</sup> uncured adhesive without sagging) > 10 <sup>14</sup> Ohm
Tensile Stress (100%)	300 psi (ca. 2.1 MPa)
Tensile Stress at Break	420 psi (ca. 2.9 MPa)
Elongation at Break	ca. 225%
Shear Stress	360 psi (ca. 2.5 MPa)
Tear Propagation	(Aluminum-to-Aluminum; adhesive thickness 2mm, test speed 50 mm/min.) ca. 13 N/mm
E-Modulus(10%)	(Type C, test speed 500 mm/min.) 623 psi (ca. 4.3 MPa)
Solvent Percentage	0%
Isocyanate Percentage	0%
Temperature Resistance	40°F to 248°F (-40°C to +120°C)
Temperature Resistance	356°F (+180°C)
Application Temperature	41°F to 95°F (+5°C to +35°C)
UV and Weather Resistance	Very good
Color	Black
Packaging (Note: Sizes subject to change):	
<b>STORAGE STABILITY</b>	<b>Bostik® 70-08A</b> — 20 oz. sausage, 5 gallon pail, 52 gallon drum
<b>Bostik® 70-08A / Simson ISR 70-08</b> may be stored in a closed (unopened) container in a dry place at temperatures between 41°F to 86°F (5°C to 30°C) as follows:	<b>Simson ISR 70-08</b> — 290 ml cartridge, 400 ml sausage, 20 L pail, 200 L drum
41°F to 86°F (5°C to 30°C) as follows:	
Cartridges — 18 months	
Sausages — 12 months	
5 Gallon Pails — 9 months	
52 Gallon Drums — 9 months	
<b>SAFETY PRECAUTIONS</b>	No specific precautions required. Consult safety data sheet.
<b>TRANSPORT CLASSIFICATION</b>	Not applicable.

Distributed by / Distributed by:

**Bostik, Inc.**  
211 Station Street  
Middletown, MA, 01949-2128 USA  
Technical Service: 800-71BOSTIK  
FAX: 978-750-2293  
www.bostik-us.com

Manufactured by:

**Bostik B.V.**  
Division Industry  
P.O. Box 303  
5201 AH 's-Hertogenbosch  
The Netherlands  
Tel.: +31 (0)73 6244 330  
Fax: +31 (0)73 6244 331  
E-Mail: info@bostik.nl  
Internet: www.bostik.nl


## IMPORTANT NOTICE

All statements, technical information and recommendations set forth herein are based on tests which Bostik, Inc. believes to be reliable. However, Bostik, Inc. does not guarantee their accuracy or completeness. The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. Any sales of this product shall be on terms and conditions set forth on Bostik's order acknowledgment. Bostik, Inc. warrants that the product conforms with Bostik, Inc. written specifications, and is free from defects. BOSTIK, INC. DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, THE BUYER'S SOLE REMEDY FOR NONCONFORMANCE WITH THIS WARRANTY SHALL BE A RETURN TO THE SELLER FOR A REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK, INC. BE LIABLE FOR DIRECT, CONSEQUENTIAL, ECONOMIC OR OTHER DAMAGES.

All figures, recommendations and safety precautions are based on thorough investigations and our actual experience and are without engagement. Although the documentation has been set up with most carelessness, we do not accept any responsibility for mistakes, inaccuracies or printer's errors. We reserve the right to adjust the product, whenever we feel necessary. Because the design, the quality of the substrate and the conditions during application fall beyond our control, no responsibility for executed works can be accepted on the basis of this documentation. We therefore recommend to carry out our own tests on the spot. All our deliveries are subject to the General Terms and Conditions for the members of the Netherlands Association of Rubber and Plastics Manufacturers ("Nederlandsche Vereniging van Rubber- en kunststoffabrikanten").



## INDUSTRIAL SPECIAL RANGE



# Bostik® 70-08A

# SIMSON® ISR 70-08

The Simson Industrial Special Range is a range of high tech quality products especially developed for industrial applications.

## PRODUCT

Bostik® 70-08A / Simson ISR 70-08 is a high quality product based on Silyl Modified Polymer (SMP), especially developed for bonding windscreens. Bostik® 70-08A / Simson ISR 70-08 provides a rapid and efficient way to fasten many different materials for OEM, coach works, mobile units, etc., especially where immediately or shortly after installation objects have to be moved during the manufacturing process. Bostik® 70-08A / Simson ISR 70-08 conforms to FMVSS 212.

## FEATURES

- Bostik® 70-08A / Simson ISR 70-08 combines the advantages of a tape with the advantages of a reactive system. Immediately after installation the product has a *high green strength* (a high internal strength), which results in a very heavy paste with an extremely good slump resistance. Reaction starts with moisture and results in an irreversible vulcanised adhesive. The high green strength coupled to the high tack makes the product very suitable for those applications where the parts have to be transported immediately or shortly after installation.
- Bostik® 70-08A / Simson ISR 70-08 adheres well without primer on glass and no UV resistant primer is needed when the glass-adhesive interface is UV-protected by a ceramic coating.
- Solvent-, isocyanate- and PVC-free.
- Very good UV resistance and ageing properties.
- In general, good adhesion on several substrates without the use of a primer.
- Permanent elastic within temperatures from -40°F to 248°F (-40°C to +120°C).
- Neutral and odorless curing.
- Low volume shrinkage.
- Low electrical conductivity.

## METHOD OF USE

Bostik® 70-08A / Simson ISR 70-08 can easily be extruded with a hand or air pressure gun at temperatures between 41°F to 95°F (+5°C to +35°C). The speed of application can be improved by heating up to 158°F (70°C) maximum. For good adhesion, a clean, dry and grease free surface is necessary. Cleaning of the ceramic coated layer can be done with Simson "wash" Primer M (a one-step pretreatment) or isopropyl alcohol. The pretreatment with Simson Primer M is also adequate for many closed surfaces like e.g. aluminium coated steel, polyester (GRP). For more details concerning Simson Primer M, consult the specific technical information data sheet. Within a few minutes after applying Simson Primer M, the screen can be bonded. The screen has to be bonded within 15 minutes after applying Bostik® 70-08A / Simson ISR 70-08. The drying time of the "wash primer" can be reduced to seconds if a hot air blower is used. When no ceramic coating is available or the ceramic coating doesn't supply sufficient UV protection, Simson Primer G is needed after the screen has been cleaned with isopropyl alcohol, unless a cover shields the glass-adhesive interface from UV radiation.

Cleaning tools or removing uncured residue of Bostik® 70-08A / Simson ISR 70-08 can be done with a clean colourless cloth, wetted with isopropyl alcohol. It is recommended to make a trial first to check possible attack of the substrate by isopropyl alcohol.