

## **HYPALON (CHLOROSULFONATED POLYETHELENE)**

**FEATURES:** RESISTS GOOD ACID, ALKALI AND SALT RESISTANCE, OILS AND COMMERCIAL FUELS SUCH AS DIESEL AND KEROSENE. IT RESISTS WEATHERING, SUNLIGHT AND OZONE.

**LIMITATIONS:** TEMPERATURES FROM -50°F TO 275°F.

*HYPALON IS NOT GOOD IN AROMATICS OR CHLORINATED HYDROCARBONS AND HAS POOR RESISTANCE AGAINST CHROMIC ACID AND NITRIC ACID.*

## **RED RUBBER**

**COLOR:** RED

**FEATURES:** A GENERAL SERVICE SBR RUBBER COMPOUND OF EXCELLENT QUALITY. THIS HEAT RESISTANT MATERIAL HAS BEEN CALENDERED AND VULCANIZED UNDER THE STRICTEST CONTROL.

**EQUIPMENT:** ALL MATING FLANGES WHEREVER A QUALITY RUBBER SHEET IS REQUIRED.

**REMARKS:** DEFORMS TO UNEVEN FLANGES.

**OPERATING TEMPERATURE:** -20°F TO +170°F



## **PURE GUM**

**COLOR:** TAN

**FEATURES:** A COMPOSITION OF SPECIALLY BLENDED COMPOUNDS. SOFT, PLIABLE, CAPABLE OF FILLING FLANGE IRREGULARITIES WITH THE LIGHTEST BOLT LOADS.

**SURFACE:** SMOOTH

**EQUIPMENT:** ALL MATING FLANGES.

**LIMITATIONS:** TEMPERATURES TO 200°F / 93°C.

**REMARKS:** DEFORMS EASILY AND RECOVERS READILY.

